

527,142  
Pac'd PCT/PTO 09 MAR 2005

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
25 March 2004 (25.03.2004)

PCT

(10) International Publication Number  
WO 2004/024433 A2


- (51) International Patent Classification<sup>7</sup>: B32B V. [US/US]; 308 Camellia Street, Lake Jackson, TX 77566 (US). PATEL, Rajen, [US/US]; 114 Scarlet Oak Street, Lake Jackson, TX 77566 (US). RATTA, Varun [IN/US]; 3040, FM 518, Apt. #1553, Pearland, TX 77584 (US).
- (21) International Application Number: PCT/US2003/025395
- (22) International Filing Date: 14 August 2003 (14.08.2003) (74) Agents: WAGNER, Alan, E. et al.; Whyte Hirschboeck Dudek, S.C., 555 East Wells Street, Suite 1900, Milwaukee, WI 53202-3819 (US).
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 60/411,092 16 September 2002 (16.09.2002) US (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (71) Applicant (for all designated States except US): DOW GLOBAL TECHNOLOGIES INC. [US/US]; Washington Street, 1790 Building, Midland, MI 48674 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): SAAVEDRA, Jose, (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),

[Continued on next page]

(54) Title: HIGH CLARITY, HIGH STIFFNESS FILMS

## Modulus vs. Density of Polyethylenes

### Compression Molded Plaques



$$\text{Log}(\text{Modulus}) = -130.0787 + 270.267 \cdot \text{den} - 134.832 \cdot \text{den}^2, r^2 = 0.99$$

(57) Abstract: A multi-layer heat film having—at least three layers is disclosed wherein the film has high optical properties, high stiffness and desirable shrinkage in the cross direction. The inner layer, or layers, comprises at least one stiffening polymer selected from the group consisting of: low density polyethylene, linear low density polyethylene, high density polyethylene, blends thereof, polypropylene random copolymer, styrene/butadiene copolymer, polystyrene, ethylene-vinyl acetate copolymer and cyclic-olefin copolymer, provided that when more than one inner layer is present, the inner layers can be the same or different. The skin layers, which may be the same or different, comprise at least one of: low density polyethylene; a blend of low density polyethylene and linear low density polyethylene; a blend of low density polyethylene and very low density polyethylene; polystyrene;

ethylene-vinyl acetate copolymer; a blend of ethylene-vinyl acetate copolymer and linear low density polyethylene; cyclic-olefin copolymer; styrene-butadiene copolymer; or, polypropylene random copolymer, provided that the skin layers are devoid of a homogeneously branched polyethylene resin prepared with a single site catalyst. The inventive films have haze values of less than about 15%, a 2% secant modulus greater than about 50,000 psi and a cross directional shrinkage greater than 0%. The inventive films are made by a process that does not include post-extrusion bi-axial orientation.

WO 2004/024433 A2